



Perfect Pass is a line of quality-first maintenance & repair alloys.

WIRES • POWDERS • STICK ELECTRODES

# CHROME CARB 9109 DATA SHEET

## ULTIMATE HARD-FACING ELECTRODE FOR MEDIUM IMPACT AND ABRASION

### GENERAL CHARACTERISTICS:

High disposition rate electrode that produces smooth beads and in most cases the slag comes off all by itself. The arc is easily controlled and prevents excessive dilution with the base metal. The high chromium content of these electrodes makes the weld deposits maintain their resistance even at high temperatures.

### APPLICATIONS:

Parts subjected to severe abrasion as well as light impact such as equipment for processing soil, rock, coal cement, grinding plates, dredger teeth, conveyor screws, coal augers, agitators, earth augers, and scrapers.

### MECHANICAL PROPERTIES:

- Hardness up to 56-60 RC
- Current and Polarity: AC or DC Reverse polarity (Electrode +)
- Diameter's 1/8" – 3.25mm 5/32" – 4.0mm 3/16" – 5.0mm
- Amperage Range 80-125 100-160 125-190

### PROCEDURE:

Remove foreign material and unsound metal from surface to be welded. For best results and long service life an elastic cushion layer should be applied to the part before surfacing with this electrode Use e/0-8600 or Perfect Pass CBU for a cushion layer on carbon steels and manganese steels; on cast iron use NA 111. When making the final surface with Perfect Pass Chrome Carb 9109 keep electrode vertical to the work piece and maintain a short arc. Deposits must be kept thin, never more than two layers thick. To prevent excessive local heat build-up in the part, alternate welding area. Allow part to Cool slowly.



PO BOX 612  
GREENACRES, WA 99016  
AGRITOOLSUPPLY.COM  
800.321.5460

4230 E TRENT AVE  
SPOKANE, WA 99202  
A-LCOMPRESSEDGASES.COM  
509.534.1595



REV. 9/2023